



TENCATE Ultra™

PROPERTIES		
Nominal Weight	7.5 osy (255 gsm)	
Fabric Content	DuPont™ Kevlar®, DuPont™ Nomex® & PBO	
Weave	Ripstop	
Colors	Light Gold, Dark Gold, Black Gold & Yellow	
Finish	Super Shelltite™	
Made in America	Yes	
Certifications	NFPA 1971	
COMPOSITE TESTING		
TPP NFPA 1971 UL CERTIFIED RESULTS USING GORE® CROSSTECH® BLACK MOISTURE BARRIER	Quantum 4™ i	not available
	Quantum3D® SL2i	44 - 46
	Defender® M SL2	45 - 47
	Caldura® SL2i	42 - 44
THL NFPA 1971 UL CERTIFIED RESULTS USING GORE® CROSSTECH® BLACK MOISTURE BARRIER	Quantum 4™ i	not available
	Quantum3D® SL2i	235 - 255
	Defender® M SL2	255 - 275
	Caldura® SL2i	240 - 260
STRENGTH / DURABILITY		
Taber Abrasion	5,000 cycles	
Trap Tear	Initial	55 x 50 lbf (245 x 220 N)
	5x after wash	50 x 40 lbf (220 x 175 N)
Tensile Strength	Initial	440 x 420 lbf (1,955 x 1,865 N)
	10x after wash	320 x 310 lbf (1,420 x 1,375 N)
THERMAL TESTING		
Flame Resistance	Initial char length	0.2 x 0.2 in (5 x 5 mm)
	5x after wash	0.2 x 0.2 in (5 x 5 mm)
	After flame	0 seconds
Thermal Shrinkage	Initial char	< 1.0%
	5x after wash	< 1.0%
WATER RESISTANCE		
Water Absorption	Initial	< 1.0%
	5x after wash	< 1.0%



6501 Mall Boulevard
Union City, Georgia 30291 USA
+1 (770) 969-1000
TenCateFabrics.com

TenCateFabrics.com/Facebook
TenCateFabrics.com/Twitter
TenCateFabrics.com/YouTube
TenCateFabrics.com/LinkedIn

All listed data represent typical values. Results from multiple tests unless otherwise stated. To the best of our knowledge, all information contained herein is accurate. TenCate Protective Fabrics USA assumes no liability whatsoever for the accuracy or completeness of the information contained herein. Users of any substance must satisfy themselves by independent investigation that the material can be used safely. TenCate Protective Fabrics describes only certain hazards but cannot guarantee these are the only hazards.

Copyright © 2014 TenCate Protective Fabrics USA. TenCate is a trademark of Royal Ten Cate. Ultra is a registered trademark of TenCate Protective Fabrics USA.

Data-Sheet--Ultra.pdf | Version 11072014A